

Application No. 10/673779
Page 3

Amendment
Attorney Docket No. 011.2B-11335-US01

Amendments To The Claims:

1. (Original) A polishing composition used in precision polishing a wafer surface, the polishing composition comprising:

silicon dioxide, wherein the silicon dioxide is colloidal silica or fumed silica;

wherein, when the silicon dioxide is colloidal silica, an average primary particle diameter D_{SA} of the colloidal silica, which is obtained from a specific surface area of the colloidal silica measured by a BET method, is from 5 to 30 nm; wherein an average secondary particle diameter D_{N4} of the colloidal silica, which is measured by a laser scattering method, is from 5 to 120 nm;

wherein, when the silicon dioxide is fumed silica, an average primary particle diameter D_{SA} of the fumed silica, which is obtained from a specific surface area of the fumed silica measured by a BET method, is from 5 to 30 nm; and wherein an average secondary particle diameter D_{SA} of the fumed silica, which is measured by a laser scattering method, is from 5 to 200 nm;

an alkaline compound;

a water-soluble polymer; and

water.

2. (Original) The polishing composition according to claim 1, wherein the average primary particle diameter D_{SA} of the colloidal silica and the fumed silica is from 5 to 25 nm.

3. (Original) The polishing composition according to claim 2, wherein the average primary particle diameter D_{SA} of the colloidal silica and the fumed silica is from 5 to 20 nm.

4. (Original) The polishing composition according to claim 1, wherein the average secondary particle diameter D_{N4} of the colloidal silica is from 5 to 100 nm.

5. (Original) The polishing composition according to claim 4, wherein the average secondary particle diameter D_{N4} of the colloidal silica is from 5 to 80 nm.

Application No. 10/673779
Page 4

Amendment
Attorney Docket No. 011.2B-11335-US01

6. (Original) The polishing composition according to claim 1, wherein the silicon dioxide is colloidal silica.
7. (Original) The polishing composition according to claim 1, wherein the water-soluble polymer is at least one selected from hydroxyethyl cellulose, polyvinyl alcohol, and polyethylene oxide.
8. (Original) The polishing composition according to claim 7, wherein the water-soluble polymer is hydroxyethyl cellulose.
9. (Original) The polishing composition according to claim 8, wherein content of the hydroxyethyl cellulose in the polishing composition is from 0.005 to 1.5 wt%.
10. (Original) The polishing composition according to claim 1, wherein the alkaline compound is at least one selected from potassium hydroxide, sodium hydroxide, ammonia, tetramethylammonium hydroxide, anhydrous piperazine, and piperazine hexahydrate.
11. (Original) A method of polishing a wafer, the method comprising:
preparing a polishing composition, wherein the polishing composition includes:
silicon dioxide, wherein the silicon dioxide is colloidal silica or fumed silica;
wherein, when the silicon dioxide is colloidal silica, an average primary particle diameter D_{SA} of the colloidal silica, which is obtained from a specific surface area of the colloidal silica measured by a BET method, is from 5 to 30 nm; wherein an average secondary particle diameter D_{N4} of the colloidal silica, which is measured by a laser scattering method, is from 5 to 120 nm;
wherein, when the silicon dioxide is fumed silica, an average primary particle diameter D_{SA} of the fumed silica, which is obtained from a specific surface area of the fumed silica measured by a BET method, is from 5 to 30 nm, and wherein an average secondary particle diameter D of the fumed silica, which is measured by a laser scattering method, is from 5 to 200 nm;

Application No. 10/673779
Page 5

Amendment
Attorney Docket No. 011.2B-11335-US01

an alkaline compound;
a water-soluble polymer; and
water; and
precision polishing a surface of the wafer using the polishing composition.

Application No. 10/673779
Page 6

Amendment
Attorney Docket No. 011.2B-11335-US01

Amendments To The Drawings:

None.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.